



## 非晶块铁芯 Amorphous Block Core

### 性能参数 Electromagnetic Characteristic

饱和磁通密度 Saturation Flux Density $B_s$	1.56T (Ref.)
饱和磁致伸缩系数 Saturation magnetstriction $\lambda_s$	27ppm
铁损 Core Lose $P_{cm}$	2.3 W/kg (Ref.) at 10 kHz, 0.1T
居里温度 Curie temperature $T_c$	392 deg.C (Ref.)
最高工作温度 Maximum operation temperature	130 deg.C

